

DETAILS


Company Name:	Giatec Scientific
Project Name:	High- Rise Building
Section Name:	Wall- Level 2
Sensor Name:	Surface vs. core
Tagged By:	Project Manager Joy
Pouring Time:	2020-09-01 07:07:27
Concrete Mix:	35MPa
Threshold:	75% of specified strength (26.2 MPa)




TEST RESULTS

	Cable	Body
Max Temperature:	52.71 °C	44.72 °C
Min Temperature:	16.86 °C	19.21 °C
Maturity Index:	6086.82 °C-hrs	5055.35 °C-hrs
Strength:	36.23 MPa	34.47 MPa

TEMPERATURE



MATURITY



STRENGTH

