

# CONCRETE RESISTANCE VERTICAL TEST

Report Prepared at June 22,2016 1:07 PM

## DESCRIPTION


Project Name:	Test
Date Created:	January 01,2014 7:59 AM
Concrete Resist Unit:	Kohm.cm
Length Unit:	cm
Temperature Unit:	°C
Temperature Correction:	On
Number of Nodes (X):	4
Node Spacing (X):	50
Number of Nodes (Y):	4
Node Spacing (Y):	50



## SUMMARY

Measurement Range(ohm.m)	Area(%)
< 50	0.0
50 to 100	12.5
100 to 200	0.0
> 200	87.5

## CONCRETE RESISTANCE VERTICAL CONTOUR MAP



signature

Report Generated by Giatec iCOR™

Tabulated file in CSV format is enclosed

## CONCRETE RESISTANCE VERTICAL TEST RESULTS - RAW DATA

X	Y	Concrete Resist (Kohm.cm)	Temperature (°C)	RH	Duration (sec)	Cover (cm)
0	0	1435.0	15.5	33%	6	3
50	0	115.58508	13.5	36%	6	3
100	0	1109.163	10.5	42%	6	3
150	0	580.242	17.5	33%	6	3
0	50	757.918	16.0	33%	6	3
50	50	1029.113	18.0	31%	6	3
100	50	479.978	15.0	36%	6	3
150	50	308.443	16.0	44%	6	3
0	100	432.766	15.0	36%	6	3
50	100	366.596	12.0	41%	6	3
100	100	323.306	13.0	36%	6	3
150	100	270.045	11.0	41%	6	3
0	150	441.647	12.0	39%	6	3
50	150	246.289	16.0	34%	6	3
100	150	189.803	17.0	32%	6	3
150	150	229.7694	12.0	39%	6	3